



# Lubricool™ 250B

## Synthetic wire drawing lubricant



### Description

Lubricool 250B is a high performance, fully synthetic lubricant designed for the drawing of fine and super fine copper and plated copper wires. By utilising fully water soluble synthetic additive technologies Lubricool 250B overcomes many of the issues associated with mineral oil based emulsions such as filter binding, enamelled wire rejections, oil separation and insoluble copper soap formation.

Careful selection of lubricity additives and corrosion inhibitors delivers a highly detergent product that is resistant to degradation and destabilisation by metals and metal ions without compromising foaming characteristics. This results in outstanding machine cleanliness and maximum life.

Lubricool 250B is recommended for drawing plain and plated copper wires on single and multi-wire machines.

Lubricool 250B is also ideally suited for the drawing of enamelled wires.

### Features and benefits

- Excellent lubrication properties reduce wear on dies and cones and increase drawing speeds
- Reduces wire break frequency, minimizing downtime and allowing more full reels of wire to be produced
- Outstanding detergency keeps machines clean and free from deposit build up
- Drawn wire is smooth, bright and clean
- Good resistance to bacterial and fungal attack
- Low foam characteristics
- Ease of filtration allows efficient removal of metallic fines
- Low consumption rates

Global specialists in high-performance lubricants

**Metalube Limited**, 4 Huntsman Drive, Northbank Industrial Park, Irlam, Manchester M44 5EG, UK  
Tel: +44 (0)161 775 7771 Fax: +44 (0)161 775 7511 post@metalube.co.uk www.metalube.co.uk

Company registration number: 2263118; Company registered in England VAT registration number GB108244927000



Cert No 2367QM8001



# Lubricool™ 250B

## Recommended instructions for use

Being fully synthetic Lubricool 250B is not compatible with mineral oil based emulsions. Machines should be cleaned and flushed to remove residues of previously used lubricants.

For sensitive applications the use of deionized water is recommended. If de-ionised water is not available then make-up water should have a low salt content (conductivity <150 µS).

Lubricool 250B functions by an inverse solubility mechanism therefore bulk operating solution temperatures should be controlled to 30 - 40 °C to prevent resolubilisation problems.

To prepare a solution always add Lubricool 250B concentrate to water with adequate agitation – **never** add water to the concentrate.

For further information consult the Metalube wire drawing lubricants guide.

## Dilution range

Single Wire	Finishing	0.050mm - 0.150mm	2% – 4%
Single Wire	Finishing	0.150mm - 0.300mm	4% – 6%
Multi-Wire	Finishing	0.050mm - 0.150mm	5% – 7%
Multi-Wire	Finishing	0.150mm - 0.300mm	6% – 8%

## Pack sizes

Lubricool 250B is available in 1000 litre IBC, 205 litre drums or 20 litre containers.

## Technical data (typical values)

Property	Test method	Result
Concentrate appearance	MSTM 1	Clear blue fluid
Solution appearance (5% in de-ionised water)	MSTM 9	Clear blue solution
Solution pH (5% in de-ionised water)	MSTM 18	9.6
Density at 20°C	MSTM 23	1.077 g.cm <sup>-3</sup>
Conductivity at 25°C (5% in de-ionised water)	MSTM 34	1500 µS

Global specialists in high-performance lubricants

**Metalube Limited**, 4 Huntsman Drive, Northbank Industrial Park, Irlam, Manchester M44 5EG, UK  
Tel: +44 (0)161 775 7771 Fax: +44 (0)161 775 7511 post@metalube.co.uk www.metalube.co.uk

Company registration number: 2263118; Company registered in England VAT registration number GB108244927000



Cert No 2367QM8001



## Lubricool™ 250B

### Concentration monitoring

Solution concentration is generally measured using a refractometer measuring on the Brix scale.

To obtain the actual concentration multiply the refractometer reading by the correction factor 1.85

e.g. Refractometer reading	=	3.0
Correction factor	X	1.85
Actual dilution	=	5.55%

### Storage

Store Lubricool 250B out of direct sunlight and protect from frost. Storage temperature should be controlled to between 5°C and 35°C.

The product information in this publication is based on knowledge and experience at the time of printing. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

Issue date 07-18 AJM

Global specialists in high-performance lubricants

**Metalube Limited**, 4 Huntsman Drive, Northbank Industrial Park, Irlam, Manchester M44 5EG, UK  
Tel: +44 (0)161 775 7771 Fax: +44 (0)161 775 7511 post@metalube.co.uk www.metalube.co.uk

Company registration number: 2263118; Company registered in England VAT registration number GB108244927000



Cert No 2367QM8001